

**WEST****End of Result Set**

Generate Collection

L2: Entry 6 of 6

File: JPAB

Mar 9, 1984

PUB-NO: JP359042781A

DOCUMENT-IDENTIFIER: JP 59042781 A

TITLE: MANUFACTURE OF CARBONACEOUS MEMBER FOR FUEL CELL

PUBN-DATE: March 9, 1984

## INVENTOR-INFORMATION:

NAME

COUNTRY

TSUNODA, KOGORO

SHIMADA, TOYOICHI

SUZUKI, YOSHIO

US-CL-CURRENT: 524/495

INT-CL (IPC): H01M 8/02; C04B 35/00; C04B 35/52

## ABSTRACT:

PURPOSE: To obtain a carbonaceous material suitable as a conductive separating plate for a phosphoric-acid-type fuel cell by using as a binder a mixture resin consisting of a vinyl phenol polymer and a phenol resin initial condensation product which has an epoxy group.

CONSTITUTION: After 40pts.wt. a paravinylphenol polymer and a novolak-type phenol resin initial condensation product are mixed, the mixture is dissolved in acetone. The thus prepared mixture resin solution used as a binder is combined with artificial graphite powder of below 150 mesh, then the mixture is kneaded in a pressure-type kneader at a load pressure of 0.5kg/cm<sup>2</sup> for 2hr while maintaining the heating temperature at 90°C. Next, the kneaded mixture is air-dried to vaporize the solvent and the dried mixture is crushed and sieved to obtain formation powder of below 80 mesh. After that, the formation powder is packed into a mold of 500mm in length before being formed into a plate by thermal pressure molding by use of a hydraulic press. Next, the thus obtained molded body, after being sliced into 8.0mm thicknesses, is subjected to preliminary heating at 180°C for 24hr in a heating device, thereafter being heated to 250°C completing hardening.

COPYRIGHT: (C)1984,JPO&amp;Japio